

Monolayer WS₂ nanopores for DNA translocation with light-adjustable diameters

Gopinath Danda¹

Paul Masih Das¹
Yung-Chien Chou¹
Jerome T. Mlack¹
William M. Parkin¹
Carl H. Naylor¹
Kazunori Fujisawa²
Tianyi Zhang²
Laura Beth Fulton¹
A T Charlie Johnson¹
Mauricio Terrones²
Marija Drndic¹

¹University of Pennsylvania, 209 S 33rd Street, Philadelphia, Pennsylvania, USA

²The Pennsylvania State University, University Park, Pennsylvania, USA

gdanda@seas.upenn.edu

Abstract

Two-dimensional materials are promising for a range of novel applications, as well as attractive testbeds for probing the physics of low-dimensional systems. Tungsten disulfide (WS₂) monolayers exhibit a direct bandgap and strong photoluminescence (PL) in the visible range, opening possibilities for advanced optoelectronic applications. Here we report the realization of two-dimensional nanometer size pores in suspended monolayer WS₂ membranes, allowing for electrical and optical response in ionic current measurements. A focused electron beam was used to fabricate nanopores in WS₂ membranes suspended on silicon-based chips and characterized using PL spectroscopy and aberration-corrected high-resolution scanning transmission electron microscopy (AC-HRSTEM). It was observed that the PL intensity of suspended WS₂ monolayers is ~10-15 times stronger when compared to substrate-supported monolayers, and low dose scanning transmission electron

microscope (STEM) viewing and drilling preserves the PL signal of WS₂ around the pore. We establish that such nanopores allow ionic conductance and DNA translocations. We also demonstrate that under low-power laser illumination in solution, WS₂ nanopores grow slowly in size at an effective rate of ~0.2-0.4 nm/s, thus providing new possibilities for atomically-controlled nanopore size using short light pulses.

Figures




Figure 1: (a) WS₂ nanopore device illustrating translocation of DNA through the nanopore under a voltage bias across the membrane. (b) Ionic current signal at bias voltage of 400 mV showing DNA translocations as reductions in ionic current. (b-inset) Change in diameter of nanopore due to laser illumination.