

Topological insulator 2D nanoflakes – A Raman investigation on electron-phonon coupling

Sarah Scheitz

Sören Buchenau, Astha Sethi, John Slimak, Tomke Glier, Pranab Das, Torben Dankwort, Lewis Akinsinde, Lorenz Kienle, Andriwo Rusydi, Clemens Ulrich und Michael Rübhausen

Department of Nanostructure and Solid State Physics, Universität Hamburg, Luruper Chaussee 149, Hamburg, Germany

sarah.scheitz@desy.de

Topological insulators (TIs) are a highly discussed new phase of quantum matter, which gained a lot of scientific interest due to their topologically protected surface states [1,2]. While the bulk is insulating those surface states remain conductive even under structural disorder and are protected against backscattering [3] making them promising materials for applications in possible spintronic devices [4]. Two suitable candidates that were identified as 3D topological insulators are Bi_2Se_3 and Bi_2Te_3 [5].

To explicitly study the properties of the conducting surface states and reduce contributions from the bulk we investigated ultrathin Bi_2X_3 ($\text{X}=\text{Se}, \text{Te}$) 2D nanoflakes with a highly increased surface to volume ratio. With regard to TI based applications, it is crucial to investigate the fundamental limits of the conducting surface states due to electron-phonon interactions. A unique technique to simultaneously study the intrinsic phononic and electronic properties of a material is Raman spectroscopy.

We have studied TI nanoflakes by means of temperature and magnetic field dependent Raman spectroscopy. For Bi_2Se_3 we observe unexpected changes in the phonon self-energies at low temperatures and high magnetic fields indicative for a coupling to electronic states. Since the conductive surface states are known to be sensitive to an applied magnetic field [6], we explain our phonon anomalies by a gap opening in the Dirac cone that enables electron-phonon coupling.

References

- [1] M. Hasan, C. Kane, Rev. Mod. Phys. 4 (2010) 3045-3067
- [2] J. Moore, Nature 7286 (2010) 194-198.
- [3] P. Roushan et al., Nature 460 (2009) 1106
- [4] D. Pesin et al., Nature Materials 11 (2010) 409
- [5] H. Zhang et al., Nature Physics 5 (2009) 438-442
- [6] X.-L. Qi, Phys. Rev. B 78 (2008) 195424

Figures




Figure 1: Upper panel: SEM micrograph of Bi_2Se_3 nanoflakes. Lower panel: Linewidth dependence of the A_{1g}^2 phonon of both materials as a function of magnetic field showing a larger effect of the field on the Bi_2Se_3 phonon. The inset cartoons show the change in the energy dispersion of a TI with applied magnetic field. The linewidth changes in the Bi_2Se_3 phonon above 3 T are explained by a coupling to an electronic transition from the lower to the upper gapped Dirac Cone.