

New strategies towards atomically-sharp GNR-based heterojunctions

M.Tenorio¹

C.Moreno¹, P.Febrrer¹, J.Castro-Esteban², J.M.A.Pruneda¹, D.Peña², A.Mugarza^{1,3}.

1. *Catalan Institute of Nanoscience and Nanotechnology (ICN2) CSIC and The Barcelona Institute of Science and Technology, Campus UAB, Bellaterra, 08193 Barcelona, Spain.*

2. *Centro de Investigación en Química Biolóxica e Materiais Moleculares (CiQUS) and Departamento de Química Orgánica, Universidade de Santiago de Compostela. Santiago de Compostela 15782, Spain.*

3. *ICREA Institució Catalana de Recerca i Estudis Avançats, Lluís Companys 23, 08010 Barcelona, Spain.*

maria.tenorio@icn2.cat

Bottom-up synthesis has shown to be a very efficient method to build graphene nanoarchitectures with atomic precision. The most illustrative example is the plethora of graphene nanoribbons (GNR) that have been created practically à la carte. Despite such impressive advances in 1D homostructures, going beyond in structural complexity has turned to be a tough challenge. In particular, the synthesis of heterostructures has been limited to 1D, with no control on size and distribution of fusing components [1]. Here we report a hierarchical on-surface synthesis method for the fabrication of graphene-based superlattice heterojunctions by laterally coupling alternating doped/undoped graphene nanoribbons. For that we harness our ability to create parallelly-aligned graphene nanoribbons superlattices [2] in order to guide the synthesis of a second GNR component, in this case an N-doped isostructural counterpart, within the empty channels of the superlattice. The final step consists on fusing the hybrid GNR array into a hybrid nanoporous graphene (h-NPG) [3]. Interestingly, the electronic structure of the final product preserves the one dimensional character of the individual components, with a rigid downshift of 0.2 eV for the N-doped GNR. The resulting structure can therefore be considered as a type II superlattice heterojunction. Our hierarchical strategy fuses the concepts of 2D nanoporous graphene nanostructures, heteroatom doping and hybrid arrays in a single, novel graphene-related material, which we expect to seed new initiatives to synthesize other complex graphene nanoarchitectures with atomic precision.

REFERENCES

- [1] J. Cai et al., Nat. Nano., 9, (2014) 896-900
- [2] C. Moreno et al., Chem. Comm., 54, (2018) 9402 – 9405
- [3] C. Moreno et al., Science, 360, (2018) 199-203

FIGURES




Figure 1: STM images of pristine AGNR superlattice, of alternated pristine AGNR and N-doped polymer superlattice, and hybrid N-doped and pristine NPG.