

# Quantum critical behaviour in magic-angle twisted bilayer graphene

Alexandre Jaoui <sup>1</sup>

Dmitri K. Efetov <sup>1,2</sup>

<sup>1</sup> ICFO - The Institute of Photonic Sciences, Castelldefels, Barcelona, 08860, Spain.

<sup>2</sup> Department für Physik der LMU, Geschwister-Scholl-Platz 1, 80539 Munich, Germany.


alexandre.jaoui@icfo.eu  
dmitri.efetov@icfo.eu

The flat bands of magic-angle twisted bilayer graphene (MATBG) host strongly-correlated electronic phases such as correlated insulators [1,2], superconductors [3] and a 'strange metal' state [4]. The latter state, believed to hold the key to a deeper understanding of the electronic properties of MATBG, is obscured by the abundance of phase transitions; so far, this state could not be unequivocally differentiated from a metal undergoing frequent electron-phonon collisions [5]. We report on transport measurements in superconducting (SC) MATBG in which the correlated insulator states were suppressed by screening [6]. The uninterrupted metallic ground state features a T-linear resistivity extending over three decades in temperature, from 40 mK to 20 K, spanning a broad range of doping including those where a correlation-driven Fermi surface reconstruction occurs [7]. This 'strange-metal' behaviour is distinguished by Planckian scattering rates and a linear magneto-resistivity. To the contrary, near charge neutrality or a fully-filled flat band, as well as for devices twisted away from the magic angle, the archetypal Fermi liquid behaviour is recovered. Our measurements demonstrate the existence of a quantum-critical phase whose fluctuations dominate the metallic ground state. Further, a transition to the 'strange metal' is observed upon suppression of the SC order, which suggests an intimate relationship between quantum fluctuations and superconductivity in MATBG.

## References

- [1] Y. Cao et al., Nature 556 (2018) 80-84.
- [2] Y. Cao et al., Nature 556 (2018) 43-50.
- [3] X. Lu et al., Nature 574 (2019) 653-657.
- [4] Y. Cao et al., Phys. Rev. Lett. 124 (2020) 07680.
- [5] H. Polshyn et al., Nature Physics 15 (2019) 1011-1016.
- [6] P. Stepanov et al., Nature 583 (2021) 375.
- [7] A. Jaoui et al. (2021) arXiv:2108.07753.

## Figure



**Figure 1: Quantum critical behaviour. A**

Schematic representation of the  $(\nu, T)$  phase diagram of hole-doped MATBG. The superconducting dome is enclosed in a 'strange' metal region which is dominated by quantum fluctuations. The canonical Fermi liquid behaviour is recovered near the boundary of the flat-band region. **b**

Temperature dependence of the resistivity for  $B = 0$  across the SC phase transition ( $\nu = -2.8$ ) and the in-field corrected resistivity for the critical field 300 mT. After suppression of the SC order, the uncovered metallic state is a 'strange' metal. **c** Evolution of the resistivity at  $\nu = -2.8$  and 40 mK vs.  $B$ . The suppression of the SC order leads to a sharp increase of the resistivity, and is followed by a linear MR up to  $B = 1$  T. The linear MR is highlighted by a solid red line.