

## Nanostructure strategies towards performance-enhanced perovskite solar cells

A. García-Martín<sup>1</sup>, Z. Hu<sup>2</sup>, L. Aigouy<sup>2</sup>, J.M. García-Martín<sup>1</sup>, M.-U. González<sup>1</sup>, H.-J. Lin<sup>2</sup>, M. Schoenauer-Sebag<sup>2</sup>, L. Billot<sup>2</sup>, P. Gredin<sup>3</sup>, M. Mortier<sup>3</sup>, Z. Chen<sup>2</sup>

<sup>1</sup> Instituto de Micro y Nanotecnología IMN-CNM, CSIC (CEI UAM+CSIC), Tres Cantos, Madrid, Spain

<sup>2</sup> LPEM, ESPCI Paris, PSL Research University, CNRS, Sorbonne Universités, Paris, France

<sup>3</sup> Chimie ParisTech, PSL Research University, CNRS, Institut de Recherche de Chimie Paris, Paris, France  
a.garcia.martin@csic.es

Organic-inorganic hybrid perovskite solar cells have attracted much attention due to their high power conversion efficiency (>23%) and low-cost fabrication. Directions to further improve these solar cells include strategies to enhance their stability and their efficiency by modifying either the perovskite absorber layer or the electron/hole transport layer. For example, the transparent electron transport layer (ETL) can be an important tuning knob influencing the charge extraction, [1] light harvesting, [2] and stability [3] in these solar cells, or the use of up-conversion nanoparticles to get better performance in the near IR part of the visible spectrum. [4] Here we present two strategies based on nanostructuration, first a fundamental study of upconversion fluorescence enhancement effects near Au nanodisks by scanning near-field optical microscopy and second the effects of a nanocolumnar TiO<sub>2</sub> layer on the performance and the stability of Cs<sub>0.05</sub>(FA<sub>0.83</sub>MA<sub>0.17</sub>)<sub>0.95</sub>Pb(I<sub>0.83</sub>Br<sub>0.17</sub>)<sub>3</sub> perovskite solar cells. For the first case, the enhancement and localization of light near the metallic structures are directly visualized by using a single Er/Yb-codoped fluorescent nanocrystal glued at the end of a sharp scanning tip. [5] For the second we find that, compared to devices with planar TiO<sub>2</sub> ETLs, the TiO<sub>2</sub> nanocolumns can significantly enhance the power conversion efficiency of the perovskite solar cells by 17 % and prolong their shelf life. By analyzing the optical properties, solar cells characteristics, as well as transport/recombination properties by impedance spectroscopy, we observed light-trapping and reduced carrier recombination in solar cells associated with the use of TiO<sub>2</sub> nanocolumn arrays. [6]

### References

- [1] S.S. Mali, et al., *Chemistry of Materials* **27**, (2015) 1541
- [2] C. Liu, et al., *Journal of Materials Chemistry A* **5**, (2017) 15970
- [3] M. Salado, et al., *Nano Energy* **35**, (2017) 215
- [4] M. Bauch et al., *Plasmonics* **9**, (2014) 781
- [5] L. Aigouy, et al., *Nanoscale* **11**, (2019) 10365
- [6] Z. Hu, et al., *ACS Appl. Mater. Interfaces* **12**, (2020) 5979